

Uses and Purposes of Various Portland Cement Chemical in Construction Industry

Mr. Dharmesh Dhabliya

VIIT Pune

dharmeshdhabliya@gmail.com

Abstract

Presently a days, nonstop efforts made on cement found that changing chemical compositions in cement show various highlights. For generally different conditions, the kinds of cement that could be made distinctly by relative proportions of the oxide compositions were not seen as adequate. Tests have been taken to add new materials to the cement known as additives, at the time of grinding or by changing fundamental raw materials during the production of cement.

Keywords: cement, grinding, chemical composition etc.

I. INTRODUCTION

India being the second biggest maker of cement additionally depends a lot on the cement business in the present time. Cement industry plays a fundamental role in the development and improvement of India. It is binding substance required while building something. The cement business offers employment to a large number of individuals in India, from workers to top engineers all some place are reliant on the cement industry for their income. India has a great deal of potential of developing in the infrastructure and construction segment which is useful for the cement business. A lot of advancement as far as production lines, plants and lodging offices is found in our nation. As it is a creating country; rise in population has seen an expansion in demands for occupations and trainings which consequently has prompted an ascent in the development of schools and organizations. As per the ongoing investigation, there are around 188 large plants and 365 little plants in India; the greater part of them situated in Rajasthan, Tamil Nadu and Andhra Pradesh. Cement request in India is required to increment with the upcoming government projects . India's cement request is probably going to arrive at 600 million tons for each annum by 2025. That day isn't extremely far away when India from being the subsequent will turn into the biggest maker of cement. Cement is a structure material and has utilized on development works. There are available of cement accessible in the market. Cement essentially accessible two forms are gray dry cement and white cement.

II. TYPES OF CEMENT THEIR USES AND PURPOSES

Portland Cement

It obtained by burning together in an extent of argillaceous that containing alumina and calcareous that containing calcium carbonate or lime materials to incomplete combination at high temperature 1450 degree C . The regular calcareous material are limestone, chalk and so forth. The argillaceous material are clay, shale , slate and so on

Since , the raw material comprise principally of lime, silica , alumina and iron oxide which is significant constituent of Portland cement. It is usually utilized kind of cement creation of cement. In the structure development, concrete is utilized for the development of pillar, section, chunk, establishment and other burden bearing component

Types of Portland cement

Ordinary Portland cement (OPC)

It has great resistance from breaking and dry shrinkage yet less resistance from chemical attack. It isn't appropriate for the construction work which is presented to sulfates in the soil. There are three grade as 33,43 and 53.

Portland Pozzolana Cement (PPC)

It very well may be created by intergrading the predetermined quantities of Portland cement clinker and pozzolana materials (15 - 35 percent by mass of Portland pozzolana cement) and limited quantity of gypsum. The various pozzolana cement delivers less heat of hydration and offer more prominent resistance from the sulfur attacks and chloride-particle penetration because of polluting influence in water than ordinary Portland cement. It helpfully utilized for sewer and sewage removal works. It is especially valuable marine and hydraulic driven development and elevated structure , under water concrete structure as bridge, dam etc.

Rapid Hardening Portland Cement (RHC)

It is fundamentally the same as OPC. The early quality is accomplished by including extreme C3S in the blend and by bringing down the C2S content in the cement. The quality of Fast Solidifying cement at age of 3 days is practically same as the 7 days quality of Conventional Portland cement. This sort of cement isn't utilized for massive concrete developments. It exposed to enormous shrinkage and water prerequisite for functionality is more. The expense of RHC is about 10% more than OPC. It is appropriate for repair of street and bridge.

**TABLE 1:
TYPES OF CEMENT AND ITS APPLICATION**

NO	TYPE OF CEMENT	IS CODE	WHERE USED
1	ORDINARY CEMENT		
	C-33 GRADE	IS:269	All general Concreting works
	C-43 GRADE	IS:8112	<u>Multistorey structures.</u> Bridges or tall structures.
	C-53 GRADE	IS:12269	<u>Prestressed concrete work</u>
2	Rapid Hardening Portland Cement	IS: 8041	Road works and Repairs.
3	Low Heat Portland Cement	IS: 12600	Mass concrete Dams
4	Portland slag cement	IS:455	Marine Structure
5	<u>Portland Pozzolana Cement</u>	IS:1489	Mass Concrete-Marine Structure and general building works
6	<u>Sulphate Resisting Portland Cement</u>	IS:12330	Marine Structures foundation in <u>Sulphate bearing soils</u>
7	Hydrophobic Cement	IS:8043	Swimming pools floor of food processing plants
8	High Alumina Cement	IS :6452	Marine Structures
9	<u>Supersulphate Cement</u>	IS:6909	Marine Structures construction of sewers

Low Heat Cement (LHC)

Low Heat Cement is less reactive than OPC and it is acquired by high extent of C₂S and less measure of C₃S and C₃A. This decrease in content as result moderate advancement of solidarity however extreme quality is same. It beginning setting time is more noteworthy than OPC. It is utilized in massive development like large footings , huge raft slabs, gravity dams & thick pavement etc.

Pozzolana Slag Cement (PSC)-

This kind of cement made 35 to 65 percent of customary Portland cement clinker and ground granulated blast furnace slag (GBFC) (industrial waste product consisting of mixture of lime, silica & alumina). It has the points of interest in producing heat less rapidly than OPC . It is appropriate for mass concreting yet inadmissible cold climate as it have high sulfate resistance, it is utilized sea water development.

Sulfate Resisting Cement

It is produced by keeping the level of C3A underneath 5%. This sort of cement is utilized where the structure is inclined to extreme sulfate attacks.




Fig 1: Portland cement composition

III. CONCLUSION

The above strategy produces broadly useful Portland cement that is utilized for most development purposes. It an important structure material has achieved an revolution in the development business. Its predominance over different cements has been because of its solid nature, great water driven properties and the capacity to convey huge extent of total. Aside from this, its manufacturing can possibly change over the modern side-effects to raw materials.

REFERENCES

- [1] E.-H. Kadri, S. Kenai, K. Ezziane, R. Siddique, and G. De Schutter, “Influence of metakaolin and silica fume on the heat of hydration and compressive strength development of mortar,” *Applied Clay Science*, vol. 53, no. 4, pp. 704–708, 2011.
- [2] V. Indrawati and A. Manaf, “Mechanical strength of trass as supplementary cementing material,” *Journal of Physical Science*, vol. 92, no. 2, pp. 51–59, 2008.
- [3] S. H. Kosmatka, B. Kerkhoff, and W. C. Panarese, *Design and Control of Concrete Mixtures*, Portland Cement Association, Skokie, Ill, USA, 14th edition, 2002.
- [4] M. S. Mamlouk and J. P. Zaniewski, *Materials for Civil and Construction Engineers*, Prentice Hall, Upper Saddle River, NJ, USA, 2006.
- [5] T. Punmatharith, M. Rachakornkij, A. Imyim, and M. Wecharatana, “Co-processing of grinding sludge as alternative raw material in portland cement clinker production,” *Journal of Applied Sciences*, vol. 10, no. 15, pp. 1525–1535, 2010.
- [6] D. N. Huntzinger and T. D. Eatmon, “A life-cycle assessment of Portland cement manufacturing: comparing the traditional process with alternative technologies,” *Journal of Cleaner Production*, vol. 17, no. 7, pp. 668–675, 2009.
- [7] F. M. Lea, *The Chemistry of Cement and Concrete*, Arnold Publishers, London, UK, 3rd edition, 1970.
- [8] J. F. Young, S. Mindess, R. J. Gray, and A. Bentur, *The Science and Technology of Civil Engineering Materials*, Prentice-Hall, Upper Saddle River, NJ, USA, 1998.
- [9] H. F. W. Taylor, *Cement Chemistry*, Thomas Telford, London, UK, 2nd edition, 1997.
- [10] S. H. Kosmatka and M. L. Wilson, *Design and Control of Concrete Mixtures*, Portland Cement Association, Skokie, Ill, USA, 2011.
- [11] V. Sata, C. Jaturapitakkul, and K. Kiattikomol, “Influence of pozzolan from various by-product materials on mechanical properties of high-strength concrete,” *Construction and Building Materials*, vol. 21, no. 7, pp. 1589–1598, 2007.
- [12] A. Neville, *Neville on Concrete*, ACI, Farmington Hills, Mich, USA, 2003.
- [13] R. Fernandez, F. Martirena, and K. L. Scrivener, “The origin of the pozzolanic activity of calcined clay minerals: a comparison between kaolinite, illite and montmorillonite,” *Cement and Concrete Research*, vol. 41, no. 1, pp. 113–122, 2011.
- [14] K. Ganesan, K. Rajagopal, and K. Thangavel, “Evaluation of bagasse ash as supplementary cementitious material,” *Cement and Concrete Composites*, vol. 29, no. 6, pp. 515–524, 2007.
- [15] S. Sinthaworn and P. Nimityongskul, “Quick monitoring of pozzolanic reactivity of waste ashes,” *Waste Management*, vol. 29, no. 5, pp. 1526–1531, 2009.